

# LS080S

## Description

LS080S, homopolymer made by suspension polymerization can be applied to injection, extrusion and calendaring process.

## Application

Profile, Fitting, Tile, Deco Sheet, Board Sheet, Foam Board  
Sheet, Automotive Parts, Package

Properties	Method	Unit	LS080S	Condition
Degree of Polymerization	LG Method PVC03		800±30	
K-value			61	
Particle Size	LG Method PVC04	%	Max 0.20	45 Mesh
Bulk Density	LG Method PVC01	g/cm <sup>3</sup>	0.61±0.02	
Density			1.4	23°C
Volatiles	LG Method PVC02	%	Max 0.30	