

3626

Description

Solution polymerization
Non-functionalization

Application

Tire

Key Features

High Molecular Weight, High Oil, High Tg, Processability

Properties	Condition	Unit	3626	Method
Polymer Property				
Appearance			Dark Brown	
Volatile Material		wt %	Max 0.75	ASTM D5668
Ash		wt %	Max 0.3	ASTM D5667
Bound Styrene		%	36±1.5	ASTM D5775
Vinyl Content		%	26±2	FT-IR
Oil Content (TDAE)		%	27.3±1.5	ASTM D5774
Polymer Viscosity (Unmassed)	ML1+4,100°C	MU	53±5	ASTM D1647

Precaution

It should be stored in warehouse to be protected from sunlight, heat and moisture.

Shelf life : 24 month from date of production at room temperatures not exceeding 30°C under above storage condition (Retest critical parameters like MV and others after the expiry of shelf life)

Package

35kg bale, 35kg X 36bales = 1.26MT box