

TECHNICAL DATA

Teijin Teton Films

SL

■ Characteristics

Improved dimensional stability at high temperature
(Base film : S Type)

■ Typical Applications

FPC, MTS, substrate for various coatings

■ Pretreatment

Adhesion Promotion

■ Technical Data

Item	Unit	SL Type		Test method	
Thickness	μm	38	50	JIS C2151	
Tensile strength	MD	MPa	220	210	JIS C2318
	TD		260		
Tensile elongation	MD	%	180	190	JIS C2318
	TD		130		
Thermal Shrinkage (150 deg C × 30 mins.)	MD	%	0.4	0.4	JIS C2318
	TD		-0.1		
Coefficient of friction	μs	-	0.3	0.3	JIS C7175
	μk		0.4		
Haze	%	3.0	4.0	JIS K7136	

1.The information contained herein is believed to be reliable and correct.

2.Please refer to the MSDS for product safety data.

3.Information is presented without guarantee or warranty.