

## TECHNICAL DATA

### Teijin Teton Films G2

#### ■ Characteristics

Standard type with well balanced properties for use in wide range of applications.

#### ■ Typical Applications

Drawing office, Montage, FPC, Electrical insulation, MTS, Release, DFR, Lamination

#### ■ Pretreatment

Adhesion Promotion, Release

#### ■ Technical Data

Item	Unit	G2 Type								Test method
Thickness	$\mu\text{m}$	16	19	20	23	25	38	50	JIS C2151	
Tensile strength	MD	MPa	260	260	260	260	270	270	270	JIS C2318
	TD		310	300	300	300	290	290	270	
Tensile elongation	MD	%	150	150	150	150	130	130	130	JIS C2318
	TD		100	100	100	110	110	110	110	
Thermal Shrinkage (150 deg C $\times$ 30 mins.)	MD	%	1.7	1.7	1.7	1.7	1.7	1.7	1.7	JIS C2318
	TD		1.0	0.9	0.9	0.9	0.5	0.5	0.5	
Coefficient of friction	$\mu\text{s}$	-	0.4	0.4	0.4	0.4	0.4	0.4	0.4	JIS C7175
	$\mu\text{k}$		0.3	0.3	0.3	0.3	0.3	0.3	0.3	
Haze	%	2.0	2.2	2.2	2.3	2.4	2.9	4.5	JIS K7136	

1.The information contained herein is believed to be reliable and correct.

2.Please refer to the MSDS for product safety data.

3.Information is presented without guarantee or warranty.