

## TECHNICAL DATA

### Teijin Teton Films

#### U4

#### ■ Characteristics

Milky translucent film with superior light diffusion property

#### ■ Typical Applications

Release liner, Stamping foil, Label overlay

#### ■ Pretreatment

none

#### ■ Technical Data

Item	Unit	U4 Type	Test method
Thickness	$\mu\text{m}$	50	JIS C2151
Tensile strength	MD	200	JIS C2318
	TD	210	
Tensile elongation	MD	110	JIS C2318
	TD	100	
Thermal Shrinkage (150 deg C $\times$ 30 mins.)	MD	1.0	JIS C2318
	TD	0.3	
Coefficient of friction	$\mu\text{s}$	0.3	JIS C7175
	$\mu\text{k}$	0.3	
Haze	%	86	JIS K7136

1.The information contained herein is believed to be reliable and correct.

2.Please refer to the MSDS for product safety data.

3.Information is presented without guarantee or warranty.