



# Polyfast® SA007

## Ravago Manufacturing Europe - Acrylonitrile Styrene Acrylate

### General Information

#### Product Description

ASA heat resistant grade for injection moulding application

#### General

Material Status	• Commercial: Active
Availability	• Europe
Features	• Good Heat Resistance
Processing Method	• Injection Molding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	53.0	MPa	ISO 527-2
Tensile Stress (Break)	47.0	MPa	ISO 527-2
Tensile Strain (Break)	25	%	ISO 527-2
Flexural Modulus	2750	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	13	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	100	°C	ISO 75-2/A
Vicat Softening Temperature	108	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+12	ohms·cm	IEC 60093
Electric Strength (1.00 mm, in Oil)	38	kV/mm	IEC 60243-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.6 mm		HB	
3.2 mm		HB	
Glow Wire Flammability Index (2.0 mm)	650	°C	IEC 60695-2-12

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.