

## RAVALENE® CR L 4244

Recycled Low Density Polyethylene Resin

### OVERVIEW

<b>Description</b>	Recycled black LDPE compound
<b>Applications</b>	Extrusion of blown film, non-pressure pipes & sheets
<b>Additives</b>	None intentionally added
<b>Recycled content</b>	>95%
<b>Source</b>	Post-industrial
<b>Visual</b>	Black

### PHYSICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
<b>MFI (190°C / 2.16 kg)</b>	0.5	g/10 min	ISO 1133
<b>Density (base resin)</b>	0.930	g/cm <sup>3</sup>	ISO 1183
<b>Ash content (600 °C)</b>	1	%	ISO 3451
<b>Carbon black content</b>	>1	%	Internal

### EXTRUSION GUIDELINES

<b>Recommended settings</b>	Comparable processing to standard LDPE resins. Contact your local sales representative for specific advice.
-----------------------------	--

**Note:** Properties not to be construed as specifications