



RAVAPURA® L7020

Recycled polyethylene resin

OVERVIEW

Description	LDPE compound based on post-consumer recycled (PCR) material
Applications	Blown film
Additives	Available with & without slip and anti-block added
PCR/virgin content	70% PCR / 30% virgin
Virgin polymer	LDPE
Certification	Declaration available upon request
Visual	Natural, translucent
Gel content	Low

PHYSICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
MFI (190°C / 2.16 kg)	2,0	g/10 min	ISO 1133
Density	0,915	g/cm ³	ISO 1183
Ash content (600°C)	0,5	%	ISO 3451

EXTRUSION GUIDELINES

Recommended settings	Comparable processing to standard LDPE resins. Contact your local sales representative for specific advice.
-----------------------------	--

Note: Properties not to be construed as specifications