



RavaSafe® ZH-LSF 30 UV

Ravago Manufacturing Europe - Thermoplastic

General Information

Product Description

RavaSafe® ZH-LSF 30 UV is a thermoplastic zero halogen, low smoke flame retardant compound designed for general purpose sheathing application.

This compound combines excellent processing and good mechanical properties with UV stabilization.

Typical Application: Telecom, Low and Medium power cable application

Standard norms (type of material) : EN 50363 (TM7), VDE 0207 / 0250 (HM2, HM4), BS 7655 (LTS 2), IEC 60502 (ST8) and IEC 60092-360 (SHF1)

General

Material Status	• Commercial: Active
Availability	• Europe • Latin America • North America
Additive	• Flame Retardant • UV Stabilizer
Features	• Excellent Processability • Halogen Free • UV Stabilized • Flame Retardant • Low Smoke Emission
Uses	• Wire & Cable Applications
Appearance	• Colors Available
Processing Method	• Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.55	g/cm ³	ASTM D792
Density (23°C)	1.55	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) ² (150°C/21.6 kg)	7.0	g/10 min	ISO 1133
Water Immersion - 7 days (70°C)	1.30	mg/cm ²	IEC 60811-402
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ³	9.50	MPa	IEC 60811-501
Tensile Strain ³ (Break)	190	%	IEC 60811-501
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	8.10	kN/m	BS 6469 99.1
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	48		ASTM D2240
Shore Hardness (Shore D, 15 sec)	48		ISO 868
Thermal	Nominal Value	Unit	Test Method
Temperature Index	> 310	°C	ISO 4589-3
Aging	Nominal Value	Unit	Test Method
Change in Tensile Stress			
70°C, 4 hr, in IRM 902 Oil	> -34	%	IEC 60811-404
120°C, 168 hr	17	%	IEC 60811-501
Change in Tensile Strain at Break			
70°C, 4 hr, in IRM 902 Oil	-5.0	%	IEC 60811-404
120°C, 168 hr	-9.0	%	IEC 60811-501

RavaSafe® ZH-LSF 30 UV

Ravago Manufacturing Europe - Thermoplastic

Flammability	Nominal Value	Unit	Test Method
Oxygen Index	41	%	ASTM D2863
Oxygen Index	41	%	ISO 4589-2
Acid Gas Emission Conductivity	< 2.50	µS/mm	IEC 60754-2
Acid Gas Emission pH	> 4.30		IEC 60754-2
Halogen Content	< 1	%	IEC 60754-1
Smoke Density ⁴			ASTM E662
Flaming mode : 1.50 mm	66		
Non Flaming mode : 1.50 mm	200		

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	130	°C
Cylinder Zone 2 Temp.	140	°C
Cylinder Zone 3 Temp.	150	°C
Cylinder Zone 4 Temp.	160	°C
Cylinder Zone 5 Temp.	160	°C
Adapter Temperature	165	°C
Head Temperature	170	°C
Die Temperature	170	°C

Extrusion Notes

RavaSafe® ZH-LSF 30 UV is a product able to run on standard extruders, based on low compression screw and head. This compound is supplied in aluminium foil bags. Pre-drying is not required before extrusion process.

Notes

¹ Typical properties: these are not to be construed as specifications.

² Procedure B

³ 200 mm/min

⁴ Ds max