

## RAVALENE® CR H 2042

Recycled HDPE Density Polyethylene Resin

### OVERVIEW

<b>Description</b>	Recycled Natural oxidized HDPE compound
<b>Applications</b>	Extrusion of (non-pressure) pipes, profiles, sheet. Blow molding of certain articles
<b>Additives</b>	None intentionally added
<b>Recycled content</b>	100%
<b>Source</b>	Post-industrial
<b>Visual</b>	Natural oxidized

### PHYSICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
<b>MFI (190°C / 5 kg)</b>	1.2	g/10 min	ISO 1133
<b>MFI (190°C / 21kg)</b>	22	g/10 min	ISO 1133
<b>Density</b>	0.95	g/cm <sup>3</sup>	ISO 1183
<b>Ash content</b>	0	%	ISO 3451 600 °C

### EXTRUSION GUIDELINES

<b>Recommended settings</b>	Comparable processing to standard HPDE resins. Contact your local sales representative for specific advice.
-----------------------------	--

**Note:** Properties not to be construed as specifications