



RAVAPURA® HDPE 7525

Recycled Polyethylene Resin

OVERVIEW

Description	HDPE compound based on post-consumer (PCR) material
Applications	Blow moulding of (small) bottles. Not intended for Food Contact Applications.
PCR/virgin content	75/25
Virgin polymer	HDPE
Visual	Available in natural, white, light grey and medium grey.

PHYSICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
MFI (190°C / 21.6 kg)	25	g/10 min	ISO 1133
MFI (190°C / 2.16 kg)	0.25	g/10 min	ISO 1133
Density (base resin)	0.954	g/cm ³	ISO 1183

EXTRUSION GUIDELINES

Recommended settings	Comparable processing to standard HDPE blow moulding resins. Contact your local sales representative for specific advice.
-----------------------------	---

Note: Properties not to be construed as specifications