

RAVALENE[®] CR C 7654

Recycled Linear Low Density Polyethylene Powder

OVERVIEW

Description	Recycled black LLDPE powder for rotational molding
Applications	Rotational molding
Additives	Antioxidant
Recycled content	> 95%
Source	Post-industrial, various sources
Visual	Black

PHYSICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
MFI (190°C / 2.16 kg)	4	g/10 min	ISO 1133
Density (base resin)	0.935	g/cm ³	ISO 1183
Ash content	1	%	ISO 3451 600°C
Sieve	600	µm	-

EXTRUSION GUIDELINES

Recommended settings	Comparable processing to standard LLDPE rotomolding resins. Contact your local sales representative for specific advice.
-----------------------------	---

Note: Properties not to be construed as specifications