



Hylon N2000STH2L NAT

Polyamide 6 Prime Compound

Product Description : Unfilled, High Impact Modified, Polyamide 6 Compound

Key Features : HYLON N2000STH2L NAT is high heat stabilized and lubricated PA6 compound with good toughness and stiffness properties

Process Method : Injection moulding

Uses : Recommended for general applications and purposes

Revision Date : 01.01.2023

| | Value | Unit | Standard |
|---------------------------------------|-------|----------|--------------|
| Physical | | | |
| Density | 1,06 | gr / cm3 | ISO 1183 1-A |
| Mechanical | | | |
| Tensile Stress at Break | 40 | MPa | ISO 527-1 |
| Yield Strength | 45 | MPa | ISO 527-1 |
| Elongation at Break | >70 | % | ISO 527-1 |
| Tensile Modulus | 1900 | MPa | ISO 527-1 |
| Izod Impact Strength (Notched) (23°C) | 65 | kJ/m2 | ISO 180/1A |
| Charpy Impact Strength (Notched) | 70 | kJ/m2 | ISO 179/1A |
| Flexural Modulus | 1400 | Mpa | ISO 178 |
| Flexural Strength | 50 | Mpa | ISO 178 |
| Izod Impact Strength (Unnotched) | NB | kJ/m2 | ISO 180/1A |
| Charpy Impact Strength (Unnotched) | NB | kJ/m2 | ISO 179/1A |
| Thermal | | | |
| HDT (0.45 Mpa) | 65 | °C | ISO 75B |
| HDT (1.8 Mpa) | 50 | °C | ISO 75A |
| Flammability | | | |
| Flammability (1,6 mm) | HB | * | UL 94 |
| Flammability (3,2 mm) | HB | * | UL 94 |
| Flammability (0,8 mm) | HB | * | UL 94 |



Hylon N2000STH2L NAT

Polyamide 6 Prime Compound

Drying Condition

| | |
|------------------------|-----|
| Drying Time(hr) | 2-4 |
| Drying Temperature(°C) | 90 |

Molding Condition (°C)

| | |
|-----------------------|---------|
| 1st Zone (hopper)(°C) | 220-225 |
| 2nd Zone(°C) | 225-230 |
| 3rd Zone(°C) | 230-235 |
| Nozzle(°C) | 230-235 |
| Mold Temperature(°C) | 80 |

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

Ex : BM453UF0J1000
RAVAMID R200 T53 NC