

# Ravamid<sup>®</sup> B BK

Polyamide 6  
Industrial Quality Compound

## Description:

Polyamide 6 black containing recycled material, medium viscosity, good mechanical properties, also available Heat Stabilized (H) and UV Stabilized (UV)

## General

Density	ISO 1183	1.14	g/cm <sup>3</sup>
Mold shrinkage (Parallel)		1.06	%
Mold shrinkage (Perpendicular)		1.17	%

## Thermal

HDT/A (1,82MPa)	ISO 75A	65	°C
Vicat softening point (B50 (50N))	ISO 306	205	°C

## Mechanical

Izod notched impact strength (23°C)	ISO 180/A	7	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C)	ISO 179/1eA	7	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	55	MPa
Tensile stress at break	ISO 527	45	MPa
Elongation at break	ISO 527	20	%
Flex modulus	ISO 178	2500	MPa

## Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

## Various

Humidity	ISO 960	≤0.25	%
----------	---------	-------	---