



Hylon N2035H2L NAT

Polyamide 6 Prime Compound

Product Description : 35% Glass Fiber Reinforced, Polyamide 6 Compound

Key Features : HYLON N2035H2L NAT is PA6 compound with good strength and stiffness properties

Process Method : Injection Moulding

Uses : Recommended for general applications and purposes

Revision Date : 01.01.2023

	Value	Unit	Standard
Physical			
Density	1,39	gr / cm3	ISO 1183 1-A
Mechanical			
Tensile Stress at Break	165	MPa	ISO 527-1
Elongation at Break	3,5	%	ISO 527-1
Tensile Modulus	10500	MPa	ISO 527-1
Izod Impact Strength (Notched) (23°C)	19	kJ/m2	ISO 180/1A
Charpy Impact Strength (Notched)	18	kJ/m2	ISO 179/1A
Flexural Modulus	8000	Mpa	ISO 178
Flexural Strength	235	Mpa	ISO 178
Thermal			
HDT (0.45 Mpa)	210	°C	ISO 75B
HDT (1.8 Mpa)	205	°C	ISO 75A
Vicat Softening Point (120°C/10N)	216	°C	ISO 306
Flammability			
Flammability (1,6 mm)	HB	*	UL 94

Drying Condition

Drying Time(hr) 2-4

Drying Temperature(C) 90



Hylon N2035H2L NAT

Polyamide 6 Prime Compound

Molding Condition

Barrel Rear	235-240
Barrel Center	240-250
Barrel Front	250-265
Nozzle	250-265
Mould Temperature	80

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.