



Ravamid® B GF 50 NC

Ravago Manufacturing Europe - Polyamide 6

General Information

Product Description

Polyamide 6 natural containing recycled material, 50% glass fibre reinforced, good mechanical properties, also available Heat Stabilized (H) and UV Stabilized (UV)

General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight
Recycled Content	• Yes
Appearance	• Natural Color

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Molding Shrinkage			
Across Flow	0.40	%	
Flow	0.20	%	
Humidity	< 0.10	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13000	MPa	ISO 527-1
Tensile Stress (Break)	180	MPa	ISO 527-2
Tensile Strain (Break)	1.5	%	ISO 527-2
Flexural Modulus	10000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	75	kJ/m ²	ISO 179
Notched Izod Impact Strength (23°C)	14	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	215	°C	
Flammability	Nominal Value	Unit	Test Method
Burning Rate ²	< 100	mm/min	ISO 3795
Flame Rating			UL 94
1.6 mm		HB	
3.2 mm		HB	
Glow Wire Flammability Index (2.0 mm)	650	°C	IEC 60695-2-12

Notes

¹ Typical properties: these are not to be construed as specifications.

² FMVSS 302