

# Ravamid<sup>®</sup> B T BK

Polyamide 6  
Industrial Quality Compound

## Description:

Polyamide 6 black containing recycled material, impact modified, also available UV Stabilized (UV)

## General

Density	ISO 1183	1,11	g/cm <sup>3</sup>
Linear mould shrinkage	ISO 2577	1,00	%

## Thermal

HDT/A (1,82MPa)	ISO 75A	50	°C
-----------------	---------	----	----

## Mechanical

Izod notched impact strength (23 °C)	ISO 180	10	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C)	ISO 179	9	kJ/m <sup>2</sup>
Tensile strength at yield (23 °C)	ISO 527	50	MPa
Tensile strength at break (23 °C)	ISO 527	45	MPa
Elongation at break (23 °C)	ISO 527	20	%
Flexural modulus (23 °C)	ISO 178	2000	MPa

## Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

## Various

Humidity	ISO 960	≤0.25	%
----------	---------	-------	---