

Ravamid[®] B ST NC

Polyamide 6
Industrial Quality Compound

Description:

Polyamide 6 natural, containing recycled material, high impact modified, also available UV Stabilized (UV).

General

Density	ISO 1183	1.09	g/cm ³
Linear mould shrinkage	ASTM D955	1.25	%

Thermal

HDT/A (1,82MPa)	ISO 75A	50	°C
-----------------	---------	----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	14	kJ/m ²
Charpy notched impact strength (23 °C)	ISO 179	12,5	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	50	MPa
Tensile strength at break (23 °C)	ISO 527	45	MPa
Elongation at break (23 °C)	ISO 527	20	%
Flexural modulus (23 °C)	ISO 178	2100	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

Humidity	ISO 960	≤0.25	%
----------	---------	-------	---