



Hylon N1000THL BLACK

Polyamide 66 Industrial Quality Compound

Product Description : Unfilled, Impact Modified, Black Colour, Polyamide 66 Compound

Key Features : HYLON N1000THL BLACK is heat stabilized and lubricated PA66 compound with good strength and stiffness properties

Process Method : Injection moulding

Uses : Recommended for automotive applications

Revision Date : 29.04.2022

| | Value | Unit | Standard |
|---------------------------------------|-------|----------|--------------|
| Physical | | | |
| Density | 1,10 | gr / cm3 | ISO 1183 1-A |
| Mechanical | | | |
| Tensile Stress at Break | 65 | MPa | ISO 527-1 |
| Elongation at Break | 40 | % | ISO 527-1 |
| Izod Impact Strength (Notched) (23°C) | 15 | kJ/m2 | ISO 180/1A |
| Charpy Impact Strength (Notched) | 15 | kJ/m2 | ISO 179/1A |
| Flexural Modulus | 2100 | Mpa | ISO 178 |
| Flexural Strength | 76 | Mpa | ISO 178 |
| Thermal | | | |
| HDT (0.45 Mpa) | 228 | °C | ISO 75B |
| HDT (1.8 Mpa) | 71 | °C | ISO 75A |
| Flammability | | | |
| Flammability (1,6 mm) | HB | * | UL 94 |
| Flammability (3,2 mm) | HB | * | UL 94 |

Drying Condition

Drying Time(hr) 2-4

Drying Temperature(°C) 90

Molding Condition (°C)



Hylon N1000THL BLACK

Polyamide 66 Industrial Quality Compound

| | |
|-----------------------|---------|
| 1st Zone (hopper)(°C) | 250-270 |
| 2nd Zone(°C) | 260-280 |
| 3rd Zone(°C) | 270-290 |
| Nozzle(°C) | 270-290 |
| Mold Temperature(°C) | 80 |

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

REMARK:

This TDS applies for ID of 231315.