



Ravamid® A GF 35 BK

Ravago Manufacturing Europe - Polyamide 66

General Information

General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Recycled Content	• Yes
Appearance	• Black

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Molding Shrinkage			
Across Flow	0.80	%	
Flow	0.35	%	
Humidity	< 0.15	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7500	MPa	ISO 527-1
Tensile Stress (Break)	130	MPa	ISO 527-2
Tensile Strain (Break)	5.0	%	ISO 527-2
Flexural Modulus	7200	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.5	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	45	kJ/m ²	ISO 179
Notched Izod Impact Strength (23°C)	7.5	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	210	°C	
Vicat Softening Temperature	230	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Burning Rate ²	< 100	mm/min	ISO 3795
Flame Rating			UL 94
1.6 mm	HB		
3.2 mm	HB		
Glow Wire Flammability Index (2.0 mm)	650	°C	IEC 60695-2-12

Notes

¹ Typical properties: these are not to be construed as specifications.

² FMVSS 302