

Ravamid[®] A ST NC

Polyamide 66
Industrial Quality Compound

Description:

Polyamide 66 natural, impact modified, containing recycled material, also available UV Stabilized (UV)

General

Density	ISO 1183	1.09	g/cm ³
Mold shrinkage (Parallel)		1.10	%
Mold shrinkage (Perpendicular)		1.50	%

Thermal

HDT/A (1,82MPa)	ISO 75A	60	°C
-----------------	---------	----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	13,5	kJ/m ²
Charpy notched impact strength (23 °C)	ISO 179	11.5	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	50	MPa
Tensile strength at break (23 °C)	ISO 527	48	MPa
Elongation at break (23 °C)	ISO 527	20	%
Flexural modulus (23 °C)	ISO 178	2200	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

Humidity	ISO 960	≤ 0.25	%
----------	---------	--------	---