



# Ravamid® A GF 20 BK

## Ravago Manufacturing Europe - Polyamide 66

### General Information

#### General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Recycled Content	• Yes
Appearance	• Black

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage			
Across Flow	0.90	%	
Flow	0.46	%	
Humidity	< 0.15	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5500	MPa	ISO 527-1
Tensile Stress (Break)	90.0	MPa	ISO 527-2
Tensile Strain (Break)	5.0	%	ISO 527-2
Flexural Modulus	5000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.5	kJ/m <sup>2</sup>	ISO 179
Charpy Unnotched Impact Strength (23°C)	35	kJ/m <sup>2</sup>	ISO 179
Notched Izod Impact Strength (23°C)	6.0	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	195	°C	
Vicat Softening Temperature	222	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Burning Rate <sup>2</sup>	< 100	mm/min	ISO 3795
Flame Rating			UL 94
1.6 mm		HB	
3.2 mm		HB	
Glow Wire Flammability Index (2.0 mm)	650	°C	IEC 60695-2-12

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> FMVSS 302