

Ravamid[®] A T BK

Polyamide 66
Industrial Quality Compound

Description:

Polyamide 66 black containing recycled material, impact modified, also available Heat Stabilized (H) and UV Stabilized (UV)

General

Density	ISO 1183	1.11	g/cm ³
Linear mould shrinkage	ISO 2577	1.5	%

Thermal

HDT/A (1,82MPa)	ISO 75A	65	°C
-----------------	---------	----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	10	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	55	MPa
Tensile strength at break (23 °C)	ISO 527	53	MPa
Elongation at break (23 °C)	ISO 527	23	%
Flexural modulus (23 °C)	ISO 178	2400	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

Humidity	ISO 960	≤0.25	%
----------	---------	-------	---