



Ravamid® A BK

Ravago Manufacturing Europe - Polyamide 66

General Information

General

Material Status	• Commercial: Active
Availability	• Europe
Recycled Content	• Yes
Appearance	• Black

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage - Flow	1.5	%	ASTM D955
Humidity	< 0.25	%	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	75.0	MPa	ISO 527-2
Tensile Stress (Break)	72.0	MPa	ISO 527-2
Tensile Strain (Break)	20	%	ISO 527-2
Flexural Modulus	2600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	10	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	70.0	°C	ISO 75-2/A
Vicat Softening Temperature	220	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating 1.6 mm	HB		UL 94
3.2 mm	HB		
Glow Wire Flammability Index (2.0 mm)	650	°C	IEC 60695-2-12

Notes

¹ Typical properties: these are not to be construed as specifications.