



## Enester EM-180-UF0-J1-900

### ENESTER-E

**Product Description :** Unfilled, Black Colour, General Purpose Polybutylene Terephthalate Compound

**Key Features :** ENESTER EM-180-UF0-J1-900 is heat stabilized and lubricated PBT compound with excellent strength and stiffness properties

**Process Method :** Injection moulding

**Uses :** Recommended for general applications

**Revision Date :** 01.06.2021

	Value	Unit	Standard
<b>Physical</b>			
Density	1,32	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
Tensile Stress at Break	50	MPa	ISO 527-1
Elongation at Break	15	%	ISO 527-1
Tensile Modulus	2100	MPa	ISO 527-1
Izod Impact Strength (Notched) (23°C)	5	kJ/m2	ISO 180/1A
Charpy Impact Strength (Notched)	6	kJ/m2	ISO 179/1A
Flexural Modulus	2500	Mpa	ISO 178
<b>Thermal</b>			
HDT (0.45 Mpa)	160	°C	ISO 75B
HDT (1.8 Mpa)	60	°C	ISO 75A
Vicat Softening Point ( 120°C/10N )	175	°C	ISO 306
<b>Flammability</b>			
Flammability (1,6 mm)	HB	*	UL 94
Flammability ( 3,2 mm )	HB	*	UL 94

#### Drying Condition

Drying Time(hr)	2-4
Drying Temperature(°C)	120-140



## Enester EM-180-UF0-J1-900

### ENESTER-E

---

#### Molding Condition (°C)

1st Zone (hopper)(°C)	225-235
2nd Zone(°C)	230-240
3rd Zone(°C)	235-245
Nozzle(°C)	235-245
Mold Temperature(°C)	40-80

#### Important Notice;

---

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.