



Sicoklar® E01.22

Ravago Manufacturing Europe - Polycarbonate

General Information

Product Description

PC, general purpose grade, high flow

General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	• General Purpose	• High Flow
Uses	• General Purpose	

Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	22	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.70	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	60.0	MPa	ISO 527-2
Tensile Stress (Break)	57.0	MPa	ISO 527-2
Tensile Strain (Break)	65	%	ISO 527-2
Flexural Modulus	2400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180
-30°C	7.0	kJ/m ²	
23°C	55	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	140	°C	ISO 75-2/A
Vicat Softening Temperature			
--	144	°C	ISO 306/B50
--	150	°C	ISO 306/A50
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength (1.00 mm, in Oil)	17	kV/mm	IEC 60243-1
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
3.2 mm		HB	
0.75 mm		V-2	
1.6 mm		V-2	
Glow Wire Flammability Index (2.0 mm)	850	°C	IEC 60695-2-12

Notes

¹ Typical properties: these are not to be construed as specifications.