

Aurapene® PPUFBK20

OVERVIEW

Description	Black coloured, general purpose polypropylene resin manufactured from post-consumer recycled polymer.
Visual	Black

GENERAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
Melt flow rate (230°C / 2.16 kg)	15 - 25	g/10 min	ISO 1133
Bulk density	0.5 – 0.6	kg/l	In house
Moisture	<0.1	%	In house

MECHANICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
Izod notched impact (23°C)	>3.5	kJ/m ²	ISO 180

Note: Properties not to be construed as specifications