



Data Sheet

FACTOR[®] PP LGF20 S11

Product Description

Long glass fibre reinforced Polypropylene, fibre content 20%, cutting length 11 mm, colour: black Application: Injection moulding

Properties

Property		Test Method	Unit	Typical Value
Length		-	mm	11
Density		ISO 1183	g/cm ³	1,04
Fibre Content		-	%	20
Tensile Strength	+23°C	ISO 527	MPa	80
	+80°C		MPa	45
Tensile Modulus	+23°C	ISO 527	MPa	5.000
	+80°C		MPa	3800
Tensile Elongation	+23°C	ISO 527	%	3,1
	+80°C		%	3,9
Flexural Strength	+23°C	ISO 178	MPa	110
	+80°C		MPa	65
Flexural Modulus	+23°C	ISO 178	MPa	4.800
	+80°C		MPa	2.600
Flexural Elongation	+23°C	ISO 178	%	3,1
	+80°C		%	3,7
Impact Strength (Charpy unnotched)	+23°C	ISO 179	kJ/m ²	50
	-30°C		kJ/m ²	38
Heat Deflection Temperature HDT/A		ISO 75	°C	>145
Dart Impact	23°C	DIN 53443/2		

preliminary data sheet, status 06/03
technical data subject to change



**FACT Future Advanced
Composites & Technology GmbH**
Marie-Curie-Str. 10
67661 Kaiserslautern GERMANY
+49 (0)6301 - 320 20 0
www.fact-plastics.com

The data given in this document were determined on test specimens and constitute average values provided without engagement. The data and information given are based on our knowledge and experience to date, as are any references to trademarks or other intellectual property of third parties. This data and information are not intended for use in component design, nor do they in any way constitute an implied warranty of material properties. Evaluation of the material's suitability for any specific intended application is the sole responsibility of the processor. This document supersedes all previous issues.