

## Aurapene® PPUFGY15PCR

### OVERVIEW

Description	Grey coloured, unfilled general purpose polypropylene resin manufactured from post-consumer recycled polymer
Visual	Raw grey, light grey or dark grey

### GENERAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
Melt flow rate (230°C / 2.16 kg)	10 - 20	g/10 min	ISO 1133
Bulk density	0.5 – 0.6	kg/l	In house
Moisture	<0.1	%	In house

### MECHANICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
Izod notched impact (23°C)	>4	kJ/m <sup>2</sup>	ISO 180

**Note:** Properties not to be construed as specifications