

Mafill® CR X 9044 HF P060C

Polypropylene
Industrial Quality Compound

Description:

PP compound, black, high flow

General

MFI (230°/2,16kg)	ISO 1133	54	g/10min
Density	ISO 1183	0,93	g/cm ³

Mechanical

Izod notched impact strength (23 °C)	ISO 180	4	kJ/m ²
Tensile modulus (23 °C)	ISO 527	1300	MPa
Flexural modulus (23 °C)	ISO 178	1200	MPa