

# ■ Mafill® CR CT 6344 H UV2 BLACK E20000

Polypropylene  
Industrial Quality Compound

## Description:

PPC Compound, 20% talcum, black, long term heat stabilized, UV stabilized

## General

MFI ((230°C/2,16 kg))	ASTM D1238	13	g/10min
-----------------------	------------	----	---------

## Mechanical

Izod notched impact strength (23 °C)	ISO 180	8,5	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C)	ISO 179	8	kJ/m <sup>2</sup>
Tensile strength at yield (23 °C)	ISO 527	22	MPa
Tensile modulus (23 °C)	ISO 527	1950	MPa
Flexural modulus (23 °C)	ISO 178	1800	MPa

## Various

Ash content (700 °C)	ISO 3451	20	%
----------------------	----------	----	---