



Mafill® CR XC 4841

Polypropylene
Industrial Quality Compound

Description:

Polypropylene, 65% mineral filled

General

MFI (230°/2,16kg)	ISO 1133	10	g/10min
Density	ISO 1183	1.6	g/cm ³

Thermal

Vicat softening point (B50 (50N))	ISO 306	80	°C
-----------------------------------	---------	----	----

Mechanical

Izod notched impact strength (23°C)	ISO 180	3	kJ/m ²
Tensile stress at yield	ISO 527	20	MPa
Tensile stress at break	ISO 527	13	MPa
Elongation at break	ISO 527	4	%
Flex modulus	ISO 178	3200	MPa

Remark:

Preliminary datasheet