

Mafill® CR HC 6644

Polypropylene
Industrial Quality Compound

Description:

PP homopolymer compound, 40% calcium carbonate filled with medium flow capacity, black colour

General

MFI (230°/2,16kg)	ISO 1133	20	g/10min
-------------------	----------	----	---------

Thermal

Vicat softening point (B50 (50N))	ISO 306	90	°C
-----------------------------------	---------	----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	2,5	kJ/m ²
Flexural modulus (23 °C)	ISO 178	2300	MPa

Various

Ash content		40	%
-------------	--	----	---