

Ravaplen® 60 T 44

Polypropylene
Near Prime Compound

Description:

Near prime PP Copolymer, light weight talc filled, UV stabilised, suitable for interior applications, coloured upon request

General

MFI (230°/2,16kg)	ISO 1133	20	g/10min
Density	ISO 1183	0,95	g/cm ³

Thermal

HDT/A (1,82MPa)	ISO 75A	55	°C
-----------------	---------	----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	6	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	20	MPa
Elongation at yield (23 °C)	ISO 527	6	%
Tensile modulus (23 °C)	ISO 527	1300	MPa
Flexural modulus (23 °C)	ISO 178	1500	MPa

Various

Ash content (600 °C)	ISO 3451	7	%
----------------------	----------	---	---

Remark:

PRELIMINARY DATASHEET