

Mafill® CR XT 4344

Polypropylene
Industrial Quality Compound

Description:

PP compound, 20% talc filled, black

General

MFI (230°/2,16kg)	ISO 1133	7	g/10min
Density	ISO 1183	1.06	g/cm ³

Mechanical

Izod notched impact strength (23 °C)	ISO 180	4	kJ/m ²
Flexural modulus (23 °C)	ISO 178	1700	MPa

Various

Ash content (600 °C)	ISO 3451	20	%
Mould shrinkage	internal method	0,7-1,2	%