



Ravaplen® 62 G 40-0 UV

Ravago Manufacturing Europe - Polypropylene

General Information

Product Description

PP near prime compound based on recycled and prime quality raw materials, 15% glass filled, chemically coupled, UV stabilized, natural

General

Material Status	• Commercial: Active
Availability	• Europe • North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• UV Stabilizer
Features	• Chemically Coupled • UV Stabilized
Appearance	• Natural Color

Properties ¹

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ISO 1133
Ash Content (600°C)	15	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3500	MPa	ISO 527-1
Flexural Modulus (23°C)	2700	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	100	°C	ISO 306/B50

Notes

¹ Typical properties: these are not to be construed as specifications.