

 <b>Ravapura® PP 33 20</b> Polypropylene Recycled Quality Compound	
---	---

**Description:**

PP compound based on Post Consumer Recycled material, containing minimum 33% PCR.  
Available in black or other colours upon request.

**General**

MFI (230°/2,16kg)	ISO 1133	20	g/10min
Density	ISO 1183	0.91	g/cm <sup>3</sup>

**Thermal**

Vicat softening point (B50 (50N))	ISO 306	75	°C
-----------------------------------	---------	----	----

**Mechanical**

Izod notched impact strength (23 °C)	ISO 180	7	kJ/m <sup>2</sup>
Tensile strength at yield (23 °C)	ISO 527	25	MPa
Tensile strength at break (23 °C)	ISO 527	20	MPa
Elongation at break (23 °C)	ISO 527	16	%
Tensile modulus (23 °C)	ISO 527	1200	MPa
Flexural modulus (23 °C)	ISO 178	1200	MPa
Flexural strength at yield	ISO 178	37	MPa

**Remark:**

Preliminary Data Sheet