

RAVAPURA® PP 3001

Polypropylene compound with 30% post-consumer recycled content

OVERVIEW

Description	PP compound based on post-consumer recycled (PCR) material
Applications	Extrusion
Filler type & content	Unfilled
% of total recycled content on compound	30% PCR
Certification	Declaration available upon request
Visual	Black

GENERAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
MFI (230°C / 2.16 kg)	0.5	g/10 min	ISO 1133
Ash content (600°C)	2	%	ISO 3451

MECHANICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
Charpy notched impact strength (23°C)	35	kJ/m ²	ISO 179
Charpy unnotched impact strength (23°C)	NB	kJ/m ²	ISO 179
Tensile Modulus (23°C)	1150	MPa	ISO 527

Note: Preliminary datasheet

Properties not to be construed as specifications