

# ■ Scolefin<sup>®</sup> 32 G 12-0

Polypropylene  
Prime Compound

## Description:

PPH, 20% glass filled, chemically coupled, natural

## General

MFI (230°/2,16kg)	ISO 1133	3.5	g/10min
Density	ISO 1183	1.03	g/cm <sup>3</sup>

## Thermal

HDT/A (1,82MPa)	ISO 75A	140	°C
-----------------	---------	-----	----

## Mechanical

Izod notched impact strength (23°C)	ISO 180	10	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C)	ISO 179	9	kJ/m <sup>2</sup>
Charpy unnotched impact strength (23 °C)	ISO 179	48	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	70	MPa
Elongation at break	ISO 527	6	%
Tensile modulus	ISO 527	5000	MPa
Flex modulus	ISO 178	3500	MPa