

# ■ Scolefin<sup>®</sup> 42 CB 20 V1

Polypropylene  
Prime Compound

## Description:

PP conductive for injection moulding applications

## General

MFI (230°/2,16kg)	ISO 1133	10	g/10min
Density	ISO 1183	1,01	g/cm <sup>3</sup>

## Thermal

HDT/A (1,82MPa)	ISO 75A	50	°C
-----------------	---------	----	----

## Mechanical

Charpy notched impact strength (23 °C)	ISO 179	20	kJ/m <sup>2</sup>
Charpy unnotched impact strength (23 °C)	ISO 179	NB	kJ/m <sup>2</sup>
Elongation at break (23 °C)	ISO 527	30	%
Tensile modulus (23 °C)	ISO 527	1100	MPa

## Various

Surface resistivity	IEC 60093	<10E3	Ohm
---------------------	-----------	-------	-----