



# Scolefin® 62 T 26

## Ravago Manufacturing Europe - Polypropylene

### General Information

#### Product Description

PP prime compound, 20% talcum filled, high scratch resistant, for interior automotive trims, coloured on request

#### General

Material Status	• Commercial: Active
Availability	• Europe • North America
Filler / Reinforcement	• Talc, 20% Filler by Weight
Features	• High Scratch Resistance
Uses	• Automotive Interior Trim
Appearance	• Colors Available

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ISO 1133
Ash Content (700°C)	20	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1900	MPa	ISO 527-1
Tensile Stress (Yield)	20.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Flexural Modulus	2000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	18	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	50.0	°C	ISO 306/B50

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.