



RAVATHANE

Technical Data Sheet

R130D60

Description: Product is based on standard grade saturated polyester and has strong resilience and tear resistance, excellent abrasion resistance, higher resistance to hydrolysis failure and oxidation, good stability towards solvents and light.

Application: Wheel, shoes, injection part etc.

Typical Properties

PROPERTIES	METHOD	UNITS (English Metric)	NOMINAL VALUES
Hardness	DIN 53505 – ISO 868	Shore D	60D
Density	DIN ISO 1183 – 1 A	g/cm ³	1,23
100% modulus	DIN 53504 – ISO 37	MPa	21,0
300% modulus	DIN 53504 – ISO 37	MPa	40,0
Tensile strength	DIN 53504 – ISO 37	MPa	55
Elongation at break	DIN 53504 – ISO 37	%	420
Tear strength	DIN ISO 34 – 1 B/b	N/mm	200
Abrasion Resistance	DIN ISO 4649	mm ³	35

Application Guideline (Injection Molding)

Nozzle (°C)	Metering (°C)	Compression (°C)	Feed (°C)	Pressure (Mpa)	Drying Temp. (°C)
220	215	210	200	70	90-100



Manufacturer : RAVAGO KİMYA Plastik San. ve Tic. A.Ş.



Supplier : ENPLAST Plastik Kimya San. ve Tic. A.Ş.