



# RAVATHANE

## Technical Data Sheet

### R130D65

**Description:** Product is based on standard grade saturated polyester and has strong resilience and tear resistance, excellent abrasion resistance, higher resistance to hydrolysis failure and oxidation, good stability towards solvents and light.

**Application:** Wheel, shoes, injection part etc.

### Typical Properties

PROPERTIES	METHOD	UNITS (English Metric)	NOMINAL VALUES
Hardness	DIN 53505 – ISO 868	Shore D	65D
Density	DIN ISO 1183 – 1 A	g/cm <sup>3</sup>	1,23
100% modulus	DIN 53504 – ISO 37	MPa	21
300% modulus	DIN 53504 – ISO 37	MPa	34
Tensile strength	DIN 53504 – ISO 37	MPa	49
Elongation at break	DIN 53504 – ISO 37	%	460
Tear strength	DIN ISO 34 – 1 B/b	N/mm	240
Abrasion Resistance	DIN ISO 4649	mm <sup>3</sup>	40

### Application Guideline (Injection Molding)

Nozzle (°C)	Metering (°C)	Compression (°C)	Feed (°C)	Pressure (Mpa)	Drying Temp. (°C)
220	215	210	200	70	90-100



Manufacturer : RAVAGO KİMYA Plastik San. ve Tic. A.Ş.



Supplier : ENPLAST Plastik Kimya San. ve Tic. A.Ş.