



# ENFLEX® VU-221-55A

## Ravago Manufacturing Turkey - Thermoplastic Vulcanizate

### General Information

#### Product Description

Overmoulding EPDM/PP series onto PA

#### General

Material Status	• Commercial: Active
Availability	• Europe
Uses	• Overmolding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm <sup>3</sup>	ISO 2781
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1.54	MPa	ISO 37
Tensile Stress (300% Strain)	2.40	MPa	ISO 37
Tensile Stress (Break)	3.50	MPa	ISO 37
Tensile Elongation (Break)	570	%	ISO 37
Tear Strength	25.0	kN/m	ISO 34-1
Compression Set (70°C, 22 hr)	65	%	ASTM D395B
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	55		ISO 868
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-55.0	°C	ISO 974
Maximum Dynamic Service Temperature	135	°C	

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.