



ENFLEX® VL-120-85A

Ravago Manufacturing Turkey - Thermoplastic Vulcanizate

General Information

Product Description

Standard, fully vulcanized EPDM/PP series

General

Material Status • Commercial: Active
Availability • Europe

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ISO 2781
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	10.0	MPa	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	5.10	MPa	ISO 37
Tensile Stress (300% Strain)	7.00	MPa	ISO 37
Tensile Elongation (Break)	480	%	ISO 37
Tear Strength	70.0	kN/m	ISO 34-1
Compression Set			ASTM D395B
70°C, 22 hr	38	%	
100°C, 22 hr	46	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	85		ISO 868
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-60.0	°C	ISO 974
Maximum Dynamic Service Temperature	135	°C	

Notes

¹ Typical properties: these are not to be construed as specifications.