



# ENFLEX® VL-120-90A

## Ravago Manufacturing Turkey - Thermoplastic Vulcanizate

### General Information

#### Product Description

Standard, fully vulcanized EPDM/PP series

#### General

Material Status	• Commercial: Active
Availability	• Europe

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm <sup>3</sup>	ISO 2781
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	5.30	MPa	ISO 37
Tensile Stress (300% Strain)	7.50	MPa	ISO 37
Tensile Stress (Break)	12.0	MPa	ISO 37
Tensile Elongation (Break)	480	%	ISO 37
Tear Strength	78.0	kN/m	ISO 34-1
Compression Set			ASTM D395B
23°C, 22 hr	26	%	
70°C, 22 hr	38	%	
100°C, 22 hr	47	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	90		ISO 868
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-60.0	°C	ISO 974
Maximum Dynamic Service Temperature	135	°C	

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.