



ENFLEX VX-110-50D

ENFLEX-V

Product Description :	This polyolefin based thermoplastic elastomer (TPE-V) compound is a dynamically vulcanized EPDM/PP blend with improved flow behaviour. ENFLEX® series are completely recyclable and can be processed with conventional thermoplastics machinery.
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy processing Colorable with proper MB (PE, PP, etc. based)
Process Method :	Injection/multi injection molding
Uses :	Automotive, construction, home appliances, industrial applications

	Value	Unit	Standard
Physical			
Hardness	50	SHORE D	ISO 868 (3 second)
Density	0,93	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	12,2	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	12	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	16	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	540	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	85	N/mm	ISO 34-1 Method B

Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good





ENFLEX VX-110-50D

ENFLEX-V

Drying Condition

Drying Time(hr)	2
Drying Temperature(°C)	80-90

Molding Condition (°C)

1st Zone (hopper)(°C)	170-180
2nd Zone(°C)	180-190
3rd Zone(°C)	190-200
Nozzle(°C)	200-210
Melt Temperature(°C)	210-220
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

