



## Preliminary EZPRENE VU-320-40A

### EZPRENE-V

<b>Product Description :</b>	This polyolefin based non-hygroscopic thermoplastic elastomer (TPE-V) compound is a dynamically vulcanized EPDM/PP blend with improved flow behaviour. EZPRENE® series are completely recyclable and can be processed with conventional thermoplastics machine
<b>Additive Packages :</b>	H / Heat stabilizer /
<b>Key Features :</b>	Non-hygroscopic, no pre-drying Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy processing, faster cycle time over conventional TPVs Easy colorability with proper MB (PE, PP, etc)
<b>Process Method :</b>	Extrusion, coextrusion, blow molding, sheet extrusion, injection/multi injection molding
<b>Uses :</b>	Automotive, construction, home appliances, wire&cable, industrial applications

	Value	Unit	Standard
<b>Physical</b>			
Hardness	40	SHORE A	ISO 868 (3 second)
Density	0,97	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	0,7	Mpa	ISO 37, DIN 53504
300% Modulus	1,6	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	4	Mpa	ISO 37, DIN 53504,ASTM D412
Elongation at Break	500	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	19	N/mm	ISO 34-1

#### Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair



Ravago Petrokimya Uretim A.S.



## Preliminary EZPRENE VU-320-40A

### EZPRENE-V

---

Sulphuric Acid	Good
Detergent	Good

---

#### Drying Condition

Drying Time(hr)	Not required
Drying Temperature(C)	Not required

---

#### Molding Condition (°C)

1st Zone (hopper)(°C)	170-180
2nd Zone(°C)	180-190
3rd Zone(°C)	190-200
Nozzle(°C)	200-210
Melt Temperature(°C)	210-220
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

---

#### Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

