



RAVATHANE®

Technical Data Sheet

Ravathane® 141 A90 HR

Description: Thermoplastic polyurethane based on special polyester having strong resilience and tear resistance, excellent abrasion resistance, higher resistance to hydrolysis failure and oxidation, good stability towards solvents and light.

Application: Injection molding.

Features: Low cycle time, good demoulding properties.

Typical Properties

PROPERTIES	TEST METHOD	UNITS	VALUES
Hardness	ISO 868	Shore A	91
Density	ISO 1183-1 A	g/cm ³	1.19
100% modulus	ISO 37	MPa	9
300% modulus	ISO 37	MPa	13
Tensile strength	ISO 37	MPa	28
Elongation at break	ISO 37	%	650
Tear strength	ISO 34-1 B/b	N/mm	145
Abrasion Resistance	ISO 4649	mm ³	40

Properties have been tested on injection molded plaques conditioned 24 hours at room temperature before testing.

Before processing, the pellets have to be dried at 80-90 °C for 2-4 hours. Maximum moisture content should be below 0.02%.

Application Guideline (Injection Molding)

Nozzle (°C)	Metering (°C)	Compression (°C)	Feed (°C)
180-200	180-200	180-200	180-200