



ENSOFT SD-141-65A

ENSOFT-S

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is produced with food contact compliant raw materials, medium mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Excellent ozone, UV and weathering resistance. Rubberlike elasticity in a wide temperature range. Easy colorability with proper MB (PE, PP, etc. Based)
Process Method :	Extrusion, coextrusion, sheet extrusion
Uses :	Extruded parts (seals, tubes, profiles, hoses, etc.) for automotive, construction, home appliances, furniture

	Value	Unit	Standard
Physical			
Hardness	65	SHORE A	ISO 868 (3 second)
Density	1,08	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	1,8	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	2,7	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	10,2	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	660	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	31	N/mm	ISO 34-1 Method B
Aging			
Compression Set (72h/23°C)	25	%	ISO 815
Compression Set (22h/70°C)	41	%	ISO 815
Environmental Resistance			
Ozone	Excellent		
Water	Excellent		
Alcohol	Excellent		





ENSOFT SD-141-65A

ENSOFT-S

Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

